

## TUBINO ECOLOGICO

- DISPONIBILE IN GOMITOLI
- DISPONIBILE IN MATASSE
- DISPONIBILE IN ROCCHETTI



Carico di rottura medio kg	8,408	11,748	15,123	19,065	22,996	31,274	41,569	49,767	6,704	18,922
Allungamento a rottura medio %	1464,85	1637,08	1554,71	1610,63	978,12	1127,31	1333,67	1383,28	1383,02	836,28
Sviluppo medio per Kg m	260	200	140	120	100	80	60	40	295	155
Ø n°	1	2	3	4	5	6	7	8	1S.	4G.